

Conjugated, rod-like viologen oligomers: correlation of oligomer length with conductivity and photoconductivity

Article

Supplemental Material

Creative Commons: Attribution-Noncommercial-No Derivative Works 4.0

Chen, L., Vivier, E., Eling, C. J., Babra, T. S., Bouillard, J.-S. G., Adawi, A. M., Benoit, D. M., Hartl, F. ORCID: <https://orcid.org/0000-0002-7013-5360>, Colquhoun, H. M., Efremova, O. A. and Greenland, B. W. (2018) Conjugated, rod-like viologen oligomers: correlation of oligomer length with conductivity and photoconductivity. *Synthetic Metals*, 241. pp. 31-38. ISSN 0379-6779 doi: <https://doi.org/10.1016/j.synthmet.2018.03.019> Available at <https://centaur.reading.ac.uk/77262/>

It is advisable to refer to the publisher's version if you intend to cite from the work. See [Guidance on citing](#).

Published version at: <https://www.sciencedirect.com/science/article/pii/S0379677918300729?via%3Dihub>

To link to this article DOI: <http://dx.doi.org/10.1016/j.synthmet.2018.03.019>

Publisher: Elsevier

All outputs in CentAUR are protected by Intellectual Property Rights law, including copyright law. Copyright and IPR is retained by the creators or other copyright holders. Terms and conditions for use of this material are defined in the [End User Agreement](#).

www.reading.ac.uk/centaur

CentAUR

Central Archive at the University of Reading

Reading's research outputs online

Supplementary Data

Conjugated, Rod-Like Viologen Oligomers: Correlation of Oligomer Length with Conductivity and Photoconductivity

Long Chen^a, Elodie Vivier^b, Charlotte J. Eling^{b, d}, Tahkur S. Babra^c, Jean-Sebastien G. Bouillard^{b, d}, Ali M. Adawi^{b, d}, David M. Benoit^{b, d}, František Hartl^a, Howard M. Colquhoun^a, Olga A. Efremova^{b, d, □□}, Barnaby W. Greenland^{e, □}

a) Department of Chemistry, University of Reading, Whiteknights, Reading, RG6 6AD

b) School of Mathematics and Physical Sciences, Chemistry, University of Hull, Cottingham Road, Hull, HU6 7RX

c) School of Pharmacy, University of Reading, Whiteknights, Reading, RG6 6AH

d) G. W. Gray Centre for Advanced Materials, University of Hull, Cottingham Road, Hull, HU6 7RX, UK

e) School of Life Sciences, Department of Chemistry, University of Sussex, Brighton, BN1 9QJ.

email: b.w.greenland@sussex.ac.uk O.Efremova@hull.ac.uk;

Contents

Condition for spin coating.....	2
NMR spectra for all new compounds.....	3

Table S1: Conditions for spin-coating.

	Concentration, mg mL ⁻¹	Speed, rpm	Time of spin-coating, s
Compound 1	22	1500	41
Compound 2	38	3500	41
Compound 3	21	3500	41

^1H and ^{13}C NMR spectra





Figure S1. ^1H and ^{13}C NMR spectra (in D_2O) of compound 8





Figure S2. ¹H and ¹³C NMR spectra (in D₂O) of compound 10




Figure S3. ^1H and ^{13}C NMR spectra (in CD_3OD) of compound 13








Figure S4. ^1H and ^{13}C NMR spectra (in CD_3OD) of compound **3**



(a)



(b)



(c)

Figure S5: The representative images of tapping mode AFM topograph of the films of **1** (a), **2** (b) and **3** (c) made in tapping mode. The scale bars on the right demonstrate the films are relatively smooth. No particular features that would suggest crystallization are observed.