

# *Shape-controlled continuous synthesis of metal nanostructures*

Article

Supplemental Material

Creative Commons: Attribution 3.0 (CC-BY)

Open Access

Sebastian, V., Smith, C. D. ORCID: <https://orcid.org/0000-0002-5911-5836> and Jensen, K. F. (2016) Shape-controlled continuous synthesis of metal nanostructures. *Nanoscale*, 8 (14). pp. 7534-7543. ISSN 2040-3364 doi: 10.1039/c5nr08531d Available at <https://centaur.reading.ac.uk/58364/>

It is advisable to refer to the publisher's version if you intend to cite from the work. See [Guidance on citing](#).

To link to this article DOI: <http://dx.doi.org/10.1039/c5nr08531d>

Publisher: The Royal Society of Chemistry

All outputs in CentAUR are protected by Intellectual Property Rights law, including copyright law. Copyright and IPR is retained by the creators or other copyright holders. Terms and conditions for use of this material are defined in the [End User Agreement](#).

[www.reading.ac.uk/centaur](http://www.reading.ac.uk/centaur)

**CentAUR**

Central Archive at the University of Reading


Reading's research outputs online

Supporting information


# Shape-Controlled Continuous Synthesis of Metal Nanostructures

Víctor Sebastián, Christopher D. Smith and Klavs F. Jensen.\*


\*Department of Chemical Engineering, Massachusetts Institute of Technology, 77, Massachusetts Avenue, Cambridge, MA 02139, USA.




**Fig S1.** Microfluidic system set up.



**Fig. S2.**-TEM images of Pd nanostructures obtained without liquid segmentation at different conditions  $L_2/L_1 = 1.8$  : a) 10 s, 160°C; b) 30 s, 160°C; c) 60 s, 160°C; d) 120s, 160°C; e) 120s, 130°C; f) 120s, 190°C.




**Fig. S3.**-TEM images of Pd nanostructures obtained in oxygen segmented flow ( $O_2/\text{liquid} = 3.5/1$ ), 160°C, 120s, with different  $L_2/L_1$  ratios: a) 4/1, b) 9/1.c) Statistic diagram from Pd nanorods obtained in oxygen segmented flow (oxygen/liquid= 3.5) at residence time of 120 s and reaction temperature 160 °C at different  $L_2/L_1$  ratios: 0.25- 1.8



**Fig. S4.**-TEM Images of Pd nanostructures obtained in a microfluidic reactor: (a) Pd nanoparticles obtained without CO slug flow (laminar flow) at 90 °C, residence time = 150 s. Pd nanostructures obtained with CO slug flow, residence time = 150 s: (b) 35 °C, (c) 50 °C, (d) 90 °C, (e) 130 °C and (f) 170 °C.





**Fig. S5.-** TEM images of palladium nanosheets obtained with carbon monoxide segmentation and liquid segments containing DMF and TTAB, 150 s residence time at : (a) 90 °C, low magnification image, (b) 130 °C, low magnification image, (c) 130 °C detail image, (d) 150 °C, detail image, (e) 170 °C, detail view. (f) Representation of Plasmon Resonance Peak wavelength of Pd nanostructures versus synthesis temperature.






Fig. S6.-TEM images of palladium nanosheets obtained with carbon monoxide segmentation and liquid segments containing DMF and TTAB, 150 s residence time at 90 °C. A) After 5 days of production. B) After 2 weeks of production



**Fig. S7.** a) TEM image of Pt clusters obtained under the aqueous route at 70 °C,  $P_{co} = 120$  psi and residence time = 150 s. b) TEM image of Pt clusters obtained under the aqueous route at 100 °C,  $P_{co} = 120$  psi and residence time = 150 s. c) HRTEM image from a hexagonal assembly of Pt clusters obtained under conditions describes in b). d) TEM image of Pt clusters obtained under the aqueous route at 160 °C,  $P_{co} = 120$  psi and residence time = 150 s. e-f) HRTEM images of self-assemble Pt nanocubes obtained under the non aqueous route at 200 °C, OAm/OAl = 3.8, OLA/Pt = 230,  $P_{co} = 120$  psi and residence time = 150 s



**Figure S8.** UV-Vis spectra of the clusters obtained in the aqueous route at 125 °C and a residence time of 150 s. UV-Vis measurement of as-synthesized Pt nanostructures and after 5 and 7 days. Photographs of Pt nanostructures optical appearance as a function of time.